

HARDEN Film is the sequentially biaxially stretched film whose main material is nylon 6 (polyamide). HARDEN Film GS N5152 is the grade whose slipperiness is improved.

FUTURE

- (1) Good slipperiness under high humidity
- (2) Superior in packaging machinery aptitude in high speed
- (3) There is the tendency that printability is better than corona processed products

USE

- Use for filling under high humidity
- Use for filling in high speed

General physical property of HARDEN Film N5152 type

Item		Unit	N5152 HARDENGS	N1100	Measuring method
Thickness		μm	15	15	
Haze		%	2.8	1.5	JIS K7105
Tensile breaking strength	Length	Mpa	216	206	JIS K7127
	Width		275	275	
Tensile breaking elongation	Length	%	105	100	JIS K7127
	Width		70	70	
Heat shrinkage rate (160 degrees C, 30 mins)	Length	%	3.5	1.0	JIS K6782
	Width		2.3	1.1	

(Slipperiness)

Static friction coefficient	B/B	23°C×50% RH	0.5	0.55	JIS K7125
Dynamic friction coefficient	B/B	23°C×50% RH	0.4	0.45	
		23°C×65% RH	0.68	0.82	
		23°C×80% RH	0.88	2.2	

On these data, the representative values were measured under the specialized condition at our company's film feature evaluation agency.
Surface B: Non-corona processed surface.

< N5150001 >

TOYOBO CO., LTD. Packaging Film
<http://www.toyobo.co.jp/seihin/film/>

2-8, Dojima hama 2-chome, Kita-ku, Osaka
 530-8230, JAPAN

[TEL]+81-6-6348-4156 [FAX]+91-6-6348-4159