

PYLEN Film-DL is the biaxially stretched polypropylene film to which matting atmosphere is added.

FUTURE

P4266 is a simplex matting (matte) type, and it gives quiet appearance with preventing gloss.

As corona treatment is applied to both sides, this type is superior in the antistatic properties of both sides.

USE

Print lamination

## General physical property of PYLEN Film-DL P4266 type

Item		Unit	P2732	Measuring method
Thickness		μm	20	
Haze		%	75	JIS K7105
Gloss 45°	Revolute	%	7	JIS Z8741
Surface resistivity	Involute	logΩ	13	JIS K6911
	Revolute		10.5	
Tensile breaking strength	Length	Mpa	110	JIS K7127
	Width		230	
Tensile breaking elongation	Length	%	160	JIS K7127
	Width		40	
F-5 (Stress of 5% deformation)	Length	Mpa	29	JIS K7127
	Width		65	
Dynamic friction coefficient	Involute	-	0.2	JIS K7125
	Revolute		0.2	
Heat shrinkage rate (120 degrees C, 5mins)	Length	%	3.4	JIS K6782
	Width		0	

<P426620>

On these data, the representative values were measured under the specialized condition (23 degrees C, 50%RH) at our company's film feature evaluation agency.

\*The inks may fall off when the printed thing becomes wet depending on the process condition.

Involute: corona processed surface

Revolute: Matting (matte) surface, corona processed surface

**TOYOBO CO., LTD.** Packaging Film  
<http://www.toyobo.co.jp/seihin/film/>

2-8, Dojima hama 2-chome, Kita-ku, Osaka  
 530-8230, JAPAN

[TEL]+81-6-6348-4156 [FAX]+91-6-6348-4159